



TECHNICAL DATA SHEET

Snowbright 75 ISO / Creamy colour 9.0/ 5 5 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	75%	-1/+0,5 %
Basis Weight	55 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	110 micron	+/- 4 micron
Shade	9.0 (Standard creamy)	+/- 0.4
Opacity	87	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.