



reacto[®]
CARBONLESS PAPER

reacto[®] LASER

Selbstdurchschreibepapier für den Digitaldruck (Trockentoner)
Carbonless paper for digital printing (dry toner)
Papier autocopiant pour l'impression digitale (toner sec)
Papel autocopiativo para la impresión digital (tinta sólida)

Merkmal Property Caractéristique Propiedad	Prüfnorm Standard Norme Norma	Einheit Unit Unité Unidad	Wert Value Valeur Valor			Toleranz Tolerance Tolérance Tolerancia
			CB 80	CFB 86	CF 80	
Flächengewicht Basis weight Grammage Gramaje	ISO 536	g/m ² gsm	80	86	80	± 5 %
Dicke Caliper Epaisseur Calibre	ISO 534	µm	98	105	90	± 5
Glätte Bekk (OS) Smoothness Bekk (TS) Lissé Bekk recto Lisura Bekk anverso	ISO 5627	s	35	40	70	± 20
Weißer R457 Brightness R457 Blancheur R457 Blancura R457	ISO 2470	%	103	92	93	± 3
Reißlänge längs Breaking length md Longueur de rupture SM Longitud de rotura	ISO 1924-1	m	> 5.000			
Feuchte absolut Absolute humidity Humidité absolue Humedad absoluta		%		4		± 0,3

Änderungen vorbehalten / subject to change without notice / sous réserve de modifications / sujeto a cambio sin previo aviso



Koehler Paper SE

Hauptstraße 2 · 77704 Oberkirch · Germany · Phone +49 7802 81-0 · Fax +49 7802 81-4330 · www.koehlerpaper.com