



ITC LIMITED – PSPD, UNIT: BOLLARAM

SPECIFICATION SHEET

Doc. No: SP/TES/FP/39 Ver. No: 7.0 Rev. No: 0.0 Page 1 of 1 Issue Date: 01.01.2020

Grade Name FILOBEV 1S
Grade Id FBRR/FBVR
SPEC NO 1FBRR/FBVR /MGTH/PSPD/BOL/BAR

SUBSTANCE (GSM)	CALIPER (μM)	BENDING RESISTANCE(L&W) mN		
		Tappi T 556		
Tappi T 410	Tappi T 411	MD	CD	GM
170	223	54	25	37
175	230	61	28	41
180	236	69	32	47
185	243	82	38	56
195	257	93	43	63
200	265	102	46	68
205	270	103	48	70
210	277	109	51	75
215	284	117	54	79
225	297	134	62	91
235	311	151	70	103
245	324	158	73	107
255	338	188	87	128
265	351	225	96	147
275	365	238	110	162
285	378	281	130	191
295	392	311	143	211
305	405	330	153	225
315	419	352	163	240
325	432	359	166	244
335	446	380	176	259
345	459	402	186	273
355	473	422	195	287
TOL : ± 5%	± 5%			±15%

PARAMETER	UNITS	VALUE
COBB (3 Mins)	GSM	50 MAX ZERO
TOP BACK		
QS/TM/09 , Tappi T441		
MOISTURE	%	6 ± 1
Tappi T 412		
ROUGHNESS - BENDSTEN	ml/min	250 (350 MAX) 300 (400 MAX)
(Avg.) TOP BACK		
ISO 8791-2		
EDGEWICK - LA/23	Kg/m²/Hour	1.4 MAX
TP84010		
STRETCH	%	2.2 MIN 5.5 MIN
MD		
CD		
Tappi T 494		

Construction



Note :

- 1.) All Properties are according to ITC Limited, PSPD Unit:BOL Measurements
- 2.) Test Climate 23°C ± 1 & 50% ± 2 RH
- 3.) Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples
- 4.) This product can be serviced with FSC Mix. Certificate Registration Code: SW CoC 004747 - B

ACCEPTED BY	HEAD MARKETING (PSPD)	ISSUED BY	UNIT HEAD (BOL)
SIGNATURE		SIGNATURE	