

KIPAS DUBLEX BOARD (KDB)										
PROPERTY	UNIT	GSM&STANDART	230	250	280	300	320	350	380	400
Grammage	g/m ²	ISO 536	230	250	280	300	320	350	380	400
Taber 15° CD*	mNm		1,80	2,80	3,90	5,00	5,71	7,35	8,80	10,00
Taber 15° MD*	mNm		3,8	6,0	8,6	11,0	14,0	18,0	22,0	26,0
Stiffness 15°MD	mNm	ISO 2493	6,6	10,4	14,9	19,1	24,3	31,2	38,1	45,1
Stiffness 15°CD	mNm	ISO 2493	3,1	4,9	6,8	8,7	9,9	12,7	15,3	17,3
Brightness, top	%	ISO 2470-1	78	78	78	78	78	78	78	78
Thickness	µm	ISO 534	244	265	300	324	346	387	430	452
TOLERANCES										
PROPERTY										
Stifness	- %15									
Brightness, top	-1 % +2									
Grammage	±5%									
Thickness	±5%									
* Taber figures are calculated										