

Umka Special - GT2

Technical specification / Tehnička specifikacija

GRAMMAGE / GRAMATURA	THICKNESS / DEBLJINA	STIFFNESS / KRUTOST LW5 ⁰		STIFFNESS / KRUTOST TABER 15 ⁰	
		md	cd	md	cd
g/m ²	µm	mNm	mNm	mNm	mNm
280	360	19,6	8,1	9,8	4,1
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3
500	655	97,8	37,6	46,6	17,9

TESTING METHOD / METOD TESTIRANJA	STANDARD	TOLERANCES / TOLERANCIJA
Brightness / Belina	ISO 2470	80 ± 1%
Grammage / Gramatura	ISO 536	± 2%
Thickness / Debljina	ISO 534	± 5%
Stiffness / Krutost	DIN 53122	- 15%
Tessting climate		23 ± 1°C 50 ± 2% RH
Recyclability	EN13430	in terms of the norm
Biodegradability	EN13432	in terms of the norm

RECOMMENDED PRINTING METHODS / PREPORUČENI METODI ŠTAMPE

Offset, Flexo / Ofset štampa, Flexo štampa

*L&W figures are binding, Taber figures are indicative

*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

valid from 01.01.2020