

ADIBOARD RECY XSD GOLD - GD2

index	physical	Grade Unit								
				230	250	270	300	350	400	450
Grammage		g/m²	Target	227-233	247-252	267-272	297-303	345-355	395-410	445-460
Thickness		μ m	Target	265-280	300-310	325-345	375-390	450-470	500-520	570-590
Moisture		%	Target	6.5±1.5				7.5±1.5		
fness *		mN. m	(CD) Minimum	2.5	3.0	4.0	5.2	7.6	10.6	14.5
			(MD) Minimum	5.0	6.0	8.0	10.4	15.2	21.2	29.0
Burst Index*		N. m/g	Minimum	1.8	1.8	1.8	----	----	----	----
Thickness difference (CD)		%	Maximum	5.0						
Grammage difference (CD)		%	Maximum	5.0						
Whiteness		%	Minimum	80.0						
PPS		μ m	Maximum	1.5						
Smoothness		s	Minimum	100.0						
Gloss (75°)		%	Minimum	45.0						
Printing Gloss*		%	Minimum	85.0						
Dust degree		个/m²	0.2-1.0 mm²	≤10						
			1.0-1.5mm²	≤2						
			>1.5mm²	0.0						
Foliding strength CD*		次	Target	≥15						
Ply bond*		J/m²	Minimum	120.0						
COBB (Top/Back)		g/m²	Maximum	50/120						
Ink absorbency*		%	Target	25±3						
Blister Speed		m/s	Target	1.6						