




Grade Name : CYBER XL PREMIUM (GC2)
Grade Id : CYR / CYPR / CYRF / CRAB / CRAF

SUBSTANCE (GSM)	CALIPER (μM)	BENDING RESISTANCE(L&W) mN		
QS/TM/55	QS/TM/06	QS/TM/33 Tappi T556		
Tappi T 410	Tappi T 411	MD	CD	GM
200	330	146	74	104
210	346	176	88	124
220	363	208	107	149
230	379	232	115	163
240	398	269	139	193
250	417	312	156	220
260	437	346	173	245
270	470	398	199	281
280	490	451	226	319
290	510	489	245	346
300	532	551	275	389
310	553	599	300	424
320	571	630	315	446
330	592	688	344	487
340	610	725	362	513
350	631	826	413	584
360	648	894	447	632
370	666	947	473	669
380	684	1012	506	716
390	694	1065	532	753
400	712	1136	569	804
410	722	1208	607	856
420	735	1262	639	898
TOL : ± 4%	± 5%			-15%

CONSTRUCTION



1) All Properties are according to ITC Limited, PSPD Unit:BCM Measurements
2) Test Climate 23°C ± 1 & 50% ± 2 RH
3) Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples

APPROVED BY	Head - Marketing	ISSUED BY	Head - Technical
SIGNATURE		SIGNATURE	
VERSION NO.	7.0	ISSUE DATE	01/04/2020
REVISION NO.	0.0	PAGE NO.	1 of 1