



Cartiere SACI S.p.a.

SCHEDA TECNICA – PAPIER SPEZIFIKATION - PAPER SPECIFICATIONS – FICHE TECHNIQUE

Type Paper

Perla

Grammatura <i>Substance - Flächengewicht - Grammage</i>	gr/mq	<i>Metodo prova ISO</i>	80	90	100
Carico di rottura M.D. <i>Tensile Strenght – Laufrichtung Bruchlast – Charge de rupture</i>	KN/m	1924/3	4,47	5,03	5,29
Carico di rottura C.D. <i>Tensile Strenght – Laufrichtung Bruchlast – Charge de rupture</i>	KN/m	1924/3	2,04	2,29	2,45
Allungamento M.D. <i>Elongation – Laufrichtung Streckung - Allongment</i>	%	1924/3	2	2	2
Allungamento C.D. <i>Elongation – Laufrichtung Streckung - Allongment</i>	%	1924/3	4,5	4,5	4,5
Lunghezza di rottura M.D. <i>Breaking lenght – Laufrichtung reilänge – Longueur de rupture</i>	m	1924/3	5700	5700	5400
Lunghezza di rottura C.D. <i>Breaking lenght – Laufrichtung reilänge – Longueur de rupture</i>	m	1924/3	2600	2600	2500
Media <i>Lenght – Querrichtung - Moyenne</i>	m	-	4150	4150	3950
Indice lacerazione M.D. <i>Tear index – Durchreiung – Indice de d�chirement</i>	mNm/g	1974	7	7	7
Indice lacerazione C.D. <i>Tear index – Durchreiung – Indice de d�chirement</i>	mNm/g	1974	8	8	8
Porosit� Gurley MF <i>Porosit� gurley – Porosit� Gurley – Porosit� Gurley</i>	sec	5636/5	40< x <50	50< x <60	55< x <65
Porosit� Gurley C <i>Porosit� gurley – Porosit� Gurley – Porosit� Gurley</i>	sec	5636/5	50< x <60	60< x <70	60< x <70
Cobb 60’’	gr/mq	535	30	32	34
Resistenza allo scoppio <i>Bursting Strenght – bersten – Resistance d’eclatement</i>	KPa	2758	220	230	240
Bendsten Test Top <i>Con calandra – With Calander</i>	ml/min	8791-2	170< x <230	170< x <230	170< x <230
Bendsten Test Bottom <i>Con calandra – With Calander</i>	ml/min	8791-2	370< x <430	470< x <530	470< x <530

*I valori riportati in tabella sono garantiti con un intervallo del +/- 5 %
The values, reported on the table, are guaranteed in a range of +/- 5 %
Die angegebenen Werte unterliegen einer Toleranz von +/- 5 %*

Tabella aggiornata il 03 Gennaio 2020



Paper made in Italy



100% Carta Riciclata

