

ProVantage Kraftliner



Benefits

- Excellent strength
- Optimum runnability with reduced waste
- Fewer failures and fewer stoppages
- Stable and uniform moisture and glue absorption properties
- 100% recyclable for environmentally sound packaging

End-uses

- **Food & beverage packaging:** Fruit & vegetable packaging, Agricultural produce, High-humidity & extreme-climate storage
- **Industrial packaging:** Automotive industry, Consumer durables, Chemicals, Furniture
- **Luxury packaging:** Electronics, cigarettes & tobacco
- **Heavy-duty packaging**



Food Contact	ISO 9001	ISO 14001	ISO 45001	FSC®	PEFC
•	•	•	•	•	•

Typical Values

Properties	Method	Unit of measure	Substance (g/m²)												
			100	110*	125*	135*	150	160	170*	186*	200	225	250	275	300
Moisture	ISO 287	%	7.8												
Bursting strength	ISO 2758	kPa	460	530	580	610	680	700	730	790	850	914	966	1050	1176
SCT _{CD}	ISO 9895	kN/m	2.00	2.30	2.50	2.70	3.00	3.20	3.40	3.70	4.00	4.40	5.00	5.40	6.00
Tensile stiffness index _{MD}		kNm/g	12						11						
Tensile stiffness index _{CD}		kNm/g	5												
Cobb ₆₀ (top)	ISO 535	g/m²	30												
Cobb ₆₀ (bottom)			70												
Dennison test	TAPPI 459 om-08	No.	18												
Gurley	ISO 5636-5	s	max. 150												



Mondi Świecie
Issued from 01.02.2025,
latest version available on
mymondi.mondigroup.com

Test conditions:
Typical values after conditioning,
measured at 50 ± 2% RH and 23 ± 1°C (ISO 187 : 1990)

*ECO Premium Service, fast delivery option