

ProVantage SmartKraft Brown



Benefits

- Optimal Kraftliner alternative
- Identical surface to brown KL- 100% fresh fibres on top ply
- Excellent strength
- Burst index up to 3.7
- Optimum runnability and processing properties
- Cost efficient

End-uses

- **Food & beverage packaging:** Fruit & vegetable packaging, Agricultural produce
- **Industrial packaging:** Automotive industry
- **Heavy-duty packaging**



Food Contact	ISO 9001	ISO 14001	ISO 45001	FSC®	PEFC
•	•	•	•	•	•

Typical Values

Properties	Method	Unit of measure	Substance (g/m ²)											
			100	110	125*	135*	160*	170*	180*	200	225	250	275	300
Moisture	ISO 287	%	7.8											
Bursting strength	ISO 2758	kPa	341	404	415	452	500	567	588	662	683	772	840	940
SCT _{CD}	ISO 9895	kN/m	1.80	2.00	2.20	2.50	2.90	3.20	3.30	3.60	3.90	4.40	4.90	5.40
Tensile stiffness index _{MD}		kNm/g	11											
Tensile stiffness index _{CD}		kNm/g	4.8											
Cobb ₆₀ (top)	ISO 535	g/m ²	30											
Dennison test	TAPPI 459 om-08	No.	16											



Mondi Świecie
Issued from 01.02.2025,
latest version available on
mymondi.mondigroup.com

Test conditions:
Typical values after conditioning,
measured at 50 ± 2% RH and 23 ± 1°C
(ISO 187 : 1990)

*ECO Premium Service, fast delivery option

** Substances 250-300 gsm indicating the level / final level will be determined in the 1st quarter of 2025.